

ANTICO CADORE

Antique Fir

Botanical name:

Picea Excelsa (Link)

Trade name:

Antique Fir

Area of origin:

Northern Europe

Measurements:

150-450cm 13-30cm

TH. 15-20mm

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Red Fir

Botanical name:

Picea Excelsa(Link)

Trade name:

Red Fir

Area of origin:

Northern Europe

Measurements and variations allowed:

In compliance whit EN 13489

Choice:

In compliance whit EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidization for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLLIABLE.

ANTICO CADORE

Seasoned Acacia Robinia

Botanical name:

Robinia Pseudoacacia (Link)

Trade name:

Seasoned Acacia
Robinia

Area of origin:

Central Europe

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Canadian Maple Hard Maple

Botanical name:

Acer Saccharinum (Link)

Trade name:

Canadian Maple
Hard Maple

Area of origin:

North America

Measurements and variations allowed:

In compliance whit EN 13489

Choice:

In compliance whit EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidization for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Chestnut

Botanical name:

Castanea Sativa (Mill.)

Trade name:

Chestnut

Area of origin:

Southern Europe - Russia

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

European Cherry

Botanical name:

Prunus Avium (Link)

Trade name:

European Cherry

Area of origin:

Central Europe

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Doussie Commercial Doussie

Botanical name:

Azelia Africana
Pachyloba (Smith-Harms)

Trade name:

Doussie
Commercial Doussie

Area of origin:

Central - Western Africa

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Seasoned Beech

Botanical name:

Fagus Silvatica (Link)

Trade name:

Seasoned Beech

Area of origin:

Central Europe

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Ash

Botanical name:

Fraxinus Excelsior (Link)

Trade name:

Ash

Area of origin:

Central Europe

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Iroko wood

Botanical name:

Chlorophora Excelsa
(Benth&Hook)

Trade name:

Iroko wood

Area of origin:

Central - Western Africa

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Kempas wood

Botanical name:

Kompassia Excelsa

Trade name:

Kempas wood

Area of origin:

South - East Asia

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Antique Larch

Botanical name:

Larix Decidua (Mill)

Trade name:

Antique Larch

Area of origin:

Central Europe

Measurements:

150-450cm 13-30cm

TH. 15-20mm

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidization for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Larch whit knags

Botanical name:

Larix Decidua (Mill)

Trade name:

Larch whit knags

Area of origin:

Central Europe

Measurements and variations allowed:

In compliance whit EN 13489

Choice:

In compliance whit EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Merbau wood

Botanical name:

Intsia Palembanica
or Acuminata

Trade name:

Merbau wood

Area of origin:

South - East Asia

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Italian European Walnut

Botanical name:

Junglas Regia (Link)

Trade name:

Italian - European Walnut

Area of origin:

Central - Southern Europe

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

American Red Oak

Botanical name:

Liquidambar Styraciflua

Trade name:

American Red Oak

Area of origin:

Missisipi River banks

Measurements and variations allowed:

In compliance whit EN 13489

Choice:

In compliance whit EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidization for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLLIABLE.

ANTICO CADORE

Elm Antique Elm

Botanical name:

Ulmus Campestris (Link)

Trade name:

Elm - Antique Elm

Area of origin:

North America - Europe

Measurements:

150-450cm 13-30cm

TH. 15-20mm

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Elm American Elm

Botanical name:

Ulmus Campestris (Link)

Trade name:

Elm - American Elm

Area of origin:

North America

Measurements and variations allowed:

In compliance whit EN 13489

Choice:

In compliance whit EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidization for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLLIABLE.

ANTICO CADORE

Pear Seasoned Pear

Botanical name:

Pyrus Communis (Link)

Trade name:

Pear - Seasoned Pear

Area of origin:

Russia - Europe

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Antique Oak

Botanical name:

Quercus Robur (Link)

Trade name:

Antique Oak

Area of origin:

Central Europe

Measurements:

150-450cm 13-30cm

TH. 15-20mm

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidization for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Oak Commercial Oak

Botanical name:

Quercus Robur (Link)

Trade name:

Oak - Commercial Oak

Area of origin:

Central Europe

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Antique Teak

Botanical name:

Tectona Grandis (Link)

Trade name:

Antique Teak

Area of origin:

South - East Asia

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Asian Teak

Botanical name:

Tectona Grandis (Link)

Trade name:

Asian Teak

Area of origin:

South - East Asia

Measurements and variations allowed:

In compliance whit EN 13489

Choice:

In compliance whit EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidization for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Wengè

Botanical name:

Milletia Laurentii (De Wild)

Trade name:

Wengè

Area of origin:

Central Africa

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Yang Keruing

Botanical name:

Dipterocarpus baudii
spp. (Link)

Trade name:

Yang Keruing

Area of origin:

South - East Asia

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Antique Walnut

Botanical name:

Junglas Regia (Link)

Trade name:

Antique Walnut

Area of origin:

Central - Southern Europe

Measurements:

150-450cm 13-30cm

TH. 15-20mm

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidization for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

Antique Poplar

Botanical name:

Populus Alba
Populus Nigra (Link)

Trade name:

Antique Poplar

Area of origin:

Europe

Measurements:

150-450cm 13-30cm
TH. 15-20mm

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.

ANTICO CADORE

<name>

Botanical name:

<name>

Trade name:

<name>

Area of origin:

<name>

Measurements and variations allowed:

In compliance with EN 13489

Choice:

In compliance with EN 13489

Colour shade:

Varies

Humidity on delivery:

9% ±2%

GENERAL INFORMATION:

Treatments follow traditional methods, thereby involving different processing phases and different environmental conditions can lead to variations in colour and appearance, which are acceptable as these are not standard products. Staves are joined with D4 resin, and cold-bonded using a bonding agent with 98% solid content, formaldehyde-free. Water-based colours are used. Variations from the inspected sample may also be caused by different absorption in the same wood type. Antico Cadore Srl guarantees a genuine product: the surface layer is composed of beams and boards from demolition sites and recuperated old "masi" (farms), hay-lofts and various old buildings. Shades and colours entirely depend on the place of origin of recovery and do not affect the good quality of the final product.

In compliance with the provisions of Law no. 126 of 10/04/1991 concerning "Regulations for consumer information" and with Decree no. 101 of 08/02/1997 concerning "Regulations for implementation".



CONDITION OF USE:

Maintain a constant temperature of about 18-20°C with room humidity between 50% and 60%. Initially after laying, avoid covering floors with carpets or similar to allow even oxidation for the floor. Take great care during laying not to dirty the surface with the bonding agent (if this should occur, clean it immediately using a damp cloth). When laying is completed, clean the floor again to remove dust etc.

CHECKS BEFORE LAYING:

Before laying, it is necessary to check that the humidity of the sub-floor/laying foundation complies with "properly-done laying" regulations. Check that the surface of the sub-floor is free from any substance that might be cause of separation. Before laying, the layer must check the hygrometric ratio of the parquet, technical suitability to the type of monitoring required, and that the purchased materials are appropriate. It is advisable to use the best quality bonding agents, varnishes, oils or wax and detergents, which are compatible and suited to the type of material and laying to be carried out.

MAINTENANCE AFTER LAYING:

WAXED: Remove any dust with a vacuum cleaner and polish with a single brush. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for waxed floors in the water, using one capful for each full bucket of water. It is possible to use ANTICO CADORE natural beeswax, every six months or when the floor becomes dry to the touch, as supplementary maintenance for the floor.

OILED-STAIN-RESISTANT: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for oiled floors in the water, using one capful for each full bucket of water. It is possible to repeat the oiling process using ANTICO CADORE stain-resistant oil at regular intervals (entirely according to the traffic on the floor), as supplementary maintenance.

VARNISHED: Remove any dust with a vacuum cleaner. Wash the floor using a cloth moistened with water. It is possible to dilute a non-foam neutral detergent for varnished floors in the water, using one capful for each full bucket of water.

CLAIMS:

Follow the General Conditions of Sale laid out in the "Miscellaneous" section of the Price List. In any case, once laying has started it implies the tacit acceptance of materials.

NON-OBSERVANCE OF THE AFORESAID INSTRUCTIONS MEANS THAT THE MANUFACTURER IS NOT AT ALLIABLE.